

Test Report

Report No. A221031773710107

Page 1 of 3

Company Name
Shown on Report PCBWay

Address ROOM 1105-1108, NO.2 BUILDING, EST MALL BUSINESS CENTER,
NO.698 CHANGBANG ROAD, XIACHENG DISTRICT, 310004,
HANGZHOU, CHINA

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name 样品 1
Material pcb
Sample Received Date Aug. 9, 2021
Testing Period Aug. 9, 2021-Aug. 17, 2021

Test Requested

No.	Test Item
1	Bow and twist

Test Result(s): Please see the following pages.

Approved by Annie Lang

Date Aug. 17, 2021



Annie Lang
Approved Signatory

No. RF33A28FD6

Centre Testing International Group Co., Ltd. Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

Test Report


Report No. A221031773710107

Page 2 of 3

Tested Sample(s)

Sample No.	Sample Name	Material
A2210317737101001	样品 1	pcb

Sample Photo(s)



A2210317737101001



Test Report

Report No. A221031773710107

Page 3 of 3

Test Item: Bow and twist**1. Test Equipment**

Equipment Name	Model
Feeler	(0.02-1.00) mm/17 片

2. Environmental Conditions

Temperature: 23.4°C; Humidity: 52%RH

3. Test Standard: IPC-TM-650 2.4.22C-1999**4. Test Result(s)**

Test Sample		Test Results (%)
A2210317737101001	Twist	0.26
	Bow	0.05

Remark: The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

Statement:

- 1.This report is considered invalid without approved signature, special seal and the seal on the perforation;
- 2.Company Name and Address shown on Report, the sample(s) and sample Information was/were provided by the applicant who should be responsible for the authenticity which CTI hasn't verified;
- 3.The result(s) shown in this report refer(s) only to the sample(s) tested;
- 4.Without written approval of CTI, this report can't be reproduced except in full;
- 5.In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

*** End of Report ***

