

Test Report

Report No. A221031773710112

Page 1 of 3

Company Name
Shown on Report PCBWayAddress ROOM 1105-1108, NO.2 BUILDING, EST MALL BUSINESS CENTER,
NO.698 CHANGBANG ROAD, XIACHENG DISTRICT, 310004,
HANGZHOU, CHINA

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name 样品 1
Material pcb
Sample Received Date Aug. 9, 2021
Testing Period Aug. 9, 2021-Aug. 17, 2021

Test Requested

No.	Test Item
1	Cleanliness(NaCl equivalent)

Test Result(s): Please see the following pages.

Approved by Annie LangDate Aug. 17, 2021No. RF33A28FD6
Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

Test Report


Report No. A221031773710112

Page 2 of 3

Tested Sample(s)

Sample No.	Sample Name	Material
A2210317737101001	样品 1	pcb

Sample Photo(s)



A2210317737101001



Test Report

Report No. A221031773710112

Page 3 of 3

Test Item: Cleanliness(NaCl equivalent)**1. Test Equipment**

Equipment Name	Model
Conductance Testing Instrument	S230

2. Environmental Conditions

Temperature: 22.1°C; Humidity: 56%RH

3. Test Standard: IPC-TM-650 2.3.25D**4. Test Condition**

1) Board Surface Area= Length × Width × 2

2) Solvent Composition: V(isopropyl alcohol):V(Deionized water)=3:1

5. Test Result(s)

Test Sample	Test Result (μg NaCl Eq./cm ²)
A2210317737101001	0.26

Remark: The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

Statement:

- 1.This report is considered invalid without approved signature, special seal and the seal on the perforation;
- 2.Company Name and Address shown on Report, the sample(s) and sample Information was/were provided by the applicant who should be responsible for the authenticity which CTI hasn't verified;
- 3.The result(s) shown in this report refer(s) only to the sample(s) tested;
- 4.Without written approval of CTI, this report can't be reproduced except in full;
- 5.In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.

*** End of Report ***

